

MY1 is a water-based decorative finish: bright, sandy and metallic. It is ready-to-use and needs **only one coat**. Washable and with a high hiding power. Solvent free, easy to apply and suitable both for the professional applicator and the DIYer.

COLOR PALETTE

MY1 is available in the following essences:

- Gold
- Silver
- Bronze
- Copper

MY1 Gold and **Silver** can be tinted with our colorants.

Glitter effect: obtainable by adding **Glitter Additive** to the product.

PREPARATION OF THE SURFACE

For a proper application, the surface has to be completely smooth, dry, without dust or humidity stains.

In case of **NEW SURFACES** as traditional concrete, concrete-based plasters, gypsum and plasterboard, only apply a coat of **Decoprimer**.

In case of **OLD SURFACES** as civil plaster, tempera paint and breathable paint in good conditions, it is necessary to brush the surface before applying a coat of **Decoprimer**.

In case of **OLD SURFACES** presenting incoherent or powdery conditions, or that are coated with wax or soap, it is also necessary to sandpaper the surface before applying a coat of primer **Decoprimer**.

In all above situations, the **Decoprimer** grants proper adhesion and insulation.

APPLICATION CYCLE

PRIMER

Product: **Decoprimer**

Apply one coat by roller or brush.

Mix before use.

SINGLE COAT

Product: **MY1**

Once the Decoprimer is completely dry, apply one coat of **MY1**, in the chosen base (Silver, Gold, Bronze or Copper), either pure or tinted. Use the spalter brush to apply **MY1**, with a cross pattern on small areas. Redefine the surface with nearly-dry brush.

Mix before use.

Possible coloring:

Shake the colorant pot before use.

Pour the colorant (and the **Glitter Additive** if required) into the **MY1 Silver** or **MY1 Gold** as indicated on the color chart. Stir until you obtain a perfect homogenization.

ENVIRONMENTAL CONDITIONS OF APPLICATION

During application the temperature should be included between +10 °C and +30 °C, while the relative humidity should be lower than 85%.

STORAGE

The product maintains its properties for a period of 24 months if protected from excessive heat and cold.

Storage temperature should be included between +5 °C and +30 °C.

Protect from frost.

SAFETY GUIDELINES

Avoid contact with skin and eyes. If contact occurs, rinse thoroughly with water.

Keep away from the reach of children.

For more information consult the safety data sheet.

DISPOSAL

The product must be disposed in agreement with current regulations.

Empty containers should be sent to recycling plants.

TECHNICAL DATA

Packaging	MY1: 1.25 l (0.33 US gal) – 2.5 l (0.66 US gal) 5 l (1.32 US gal) – 12.5 l (3.30 US gal) Decoprimer: 2.5 l (0.66 US gal) – 5 l (1.32 US gal) – 12.5 l (3.30 US gal) Colorant Additives: 75 ml - 400 ml
Specific weight	MY1 Gold: 1.30 kg/liter MY1 Silver: 1.22 kg/liter MY1 Bronze: 1.30 kg/liter MY1 Copper: 1.28 kg/liter Decoprimer: 1.62 kg/liter
pH	MY1: 7.5 ± 0,05 Decoprimer: 7.5 ± 0,05
Coverage	MY1: 16 m ² /2,5 liter 172 ft ² /0,66 US gal Decoprimer: 20 m ² /2,5 liter 215 ft ² /0,66 US gal
Dilution	Ready to use
Tools	MY1: Spalter brush Decoprimer: Roller or brush
Dry to the touch	6-8 hours with 20°C room temperature
VOC	MY1: <5g/l
Dir. 2004/42/CE	Cat. A/l, limit value 2010: 200 g/l Decoprimer: <20 g/l Cat. A/h, limit value 2010: 30 g/l